



GENERAL PRODUCT SPECIFICATION

Item No.	SPC152-P
-----------------	----------

Date	16-6-2017	Replaces	18-11-14	No. Pages	1
-------------	-----------	-----------------	----------	------------------	---

Product Description:

Style	2 Blanket rolls, high strength perforation every 44 cm for single or multiple/variable length pads
Item Size (each)	48 cm wide by 44 m long (100 Pads)
Color	White
Composition	100% Polypropylene
Structure	Nonwoven mat of randomly oriented Micro-fibers [4-10 micron diameters]
Technology	Meltblown, 1-ply
Absorbency	Hydrophobic + Oleophilic
Bonding	Mechanical entanglement, dimpled (no Spunbound)

Intended Application	“Half-Size” Chemical Resistant Sorbent BLANKETS for Oil & Solvent Base Liquids.
-----------------------------	--

Absorbency Capacity	231 l per bale (saturated; medium viscosity-13.5x)
----------------------------	--

Packaging Description:

Package configuration	Bale	Pkg. Weight	14.9 kg (14.8 kg)
Items per Package	2-Blanket Rolls/Bale	Pkg. Dimensions	43 cm x 43 cm x 98 cm (H)
Container type	Polybag + Twist-Tie		

Physical Properties;

Parameter	SPC Test Method	Units	Nominal	(+/-)Tolerance
Basis Weight	SPCTM-002	G/M2	350	35
Caliper	SPCTM-020	mm	5.3	0.5
Absorbency** (med.visc.)	SPCTM-004B	gL/gS	13.5	2
Tensile Strength	SPCTM-007	daN	8.6	0.8
Color	Visual	-----	White	per standard

The above properties are “nominal” values used for **PROCESS CONTROL** when the product is produced and/or inspected. Performance “nominals” may vary depending upon the specific application, and/or the environment being applied, stored, or shipped.

** The "Absorbency" Spec and "SPCTM004" test method is based on the protocol of ASTM F726, using SAE20 non-detergent as the Oil Type, medium viscosity.

Attributes	Product will be free of foreign material contamination, rips, holes, and tears.
Labeling	Each package to be clearly labeled with Company Name, Address, Item No., Date, and/or Package Code (Bar Code).
Certification	Make no changes in basic process or composition without notifying customer. Claims for non-conformance of goods must be made within 60-days of delivery.